



TECHNICAL DATA SHEET

DESCRIPTION



DIMENSION™ National Rule Compliant Alkyd Enamel is a low cost alternative synthetic enamel line with thousands of similar color matches to the original vehicle's color. DIMENSION™ National Rule Compliant Alkyd Enamel is primarily an overall refinish line.

PHYSICAL DATA


Pot Life at 70°F: 4 hours **DA666** Fisheye Eliminator ¼ to 1 oz/RTS qt.
VOC Ready to Spray: 5.0 lbs/gal **DA664** Retarder 1 capful/RTS qt.



SUBSTRATES

Properly prepared and cleaned OE painted surfaces and Western® sealers and surfacers.

MIXING



Reducer Selection Chart

DR631	50°-65°F
DR632	60°-75°F
DR633	70°-80°F
DR634	75°-90°F
DR635	85°F and above
DR636*	100°F and above

*DR636 is formulated for use in extreme tropical and desert conditions.

NOTE: Ranges based on single panel. For spot repairs, move one solvent faster. For multiple panels move one solvent slower.

APPLICATION



1. Apply 2-3 coats to hiding.
2. Apply a mist coat to even out metallics.
3. 10-15 minutes flash between coats.

HVLP	8 - 10 psi
Siphon Feed	50 - 60 psi

DRYING



Air Dry Times at 70°F

Dust Free	80 minutes
Tape Free	Overnight
To Deliver	Overnight or 12 hours after force dry

Force Dry at 140°F 30 minutes

No recommendation to apply clearcoat at this time.

BUFFING



If necessary, after 24 hours air dry, sand with 1500 or finer grit paper and buff with the appropriate compound. Buffing is easiest when done within the first 48 hours following application. Take care in sanding and polishing single-stage metallics. Aggressive sanding can distort metal appearance. Sanding should be limited to de-nibbing imperfections with 2000 to 2500 grit sandpaper.